

PATENT COOPERATION TREATY

PCT

NOTIFICATION OF ELECTION

(PCT Rule 61.2)

From the INTERNATIONAL BUREAU

To:

Assistant Commissioner for Patents
United States Patent and Trademark
Office
Box PCT
Washington, D.C. 20231
ETATS-UNIS D'AMERIQUE

in its capacity as elected Office

Date of mailing (day month year) 09 October 2000 (09.10.00)	
International application No. PCT/SE00/00047	Applicant's or agent's file reference 2000654
International filing date (day month year) 13 January 2000 (13.01.00)	Priority date (day month year) 14 January 1999 (14.01.99)
Applicant MOSBACH, Klaus et al	

1. The designated Office is hereby notified of its election made:

☒ in the demand filed with the International Preliminary Examining Authority on:
12 July 2000 (12.07.00)

☐ in a notice effecting later election filed with the International Bureau on:

2. The election ☒ was

☐ was not

made before the expiration of 19 months from the priority date or, where Rule 32 applies, within the time limit under Rule 32.2(b).

The International Bureau of WIPO
34, chemin des Colombettes
1211 Geneva 20, Switzerland

Facsimile No.: (41-22) 740.14.35

Authorized officer

R. E. Stoffel

Telephone No.: (41-22) 338.83.38

CLAIMS

1. Molecularly imprinted microspheres comprising specific binding sites, obtainable by polymerising functional monomers and crosslinkers in a reaction solvent in the presence of print molecules as templates in a surfactant-free precipitation polymerisation process, which print molecules are capable of forming non-covalent or reversible covalent interactions with said functional monomers.
2. Molecularly imprinted microspheres according to claim 1, the diameter of which are within the range of 0.01 to 10 μ m.
3. Molecularly imprinted microspheres according to claim 1, which are monodisperse.
4. A method of producing molecularly imprinted microspheres comprising specific binding sites, characterised by polymerising functional monomers and crosslinkers in a reaction solvent in the presence of print molecules as templates in a surfactant-free precipitation polymerisation process, which print molecules are capable of forming non-covalent or reversible covalent interactions with said functional monomers.
5. A method according to claim 4, wherein the total volume of polymerisable monomers and crosslinkers is kept in the range of about 0.01 to 20 % of the volume of the reaction solvent.
6. A method according to claim 4 or 5, wherein the reaction solvent is aqueous or non-aqueous.
7. A method according to claim 4 or 5, wherein said reaction solvent is composed of a single solvent component or of multiple solvent components.
8. A method according to claim 4, wherein said functional monomers have the same functionality.
9. A method according to claim 4, wherein said functional monomers have different functionality.

10. A method according to claim 4 or 5, wherein the solubility of the print molecules in the reaction solvent is adjusted by changing the composition of the reaction solvent.

5 11. A method according to claim 4, wherein the polymerisation is induced by heat, UV radiation, γ radiation and/or chemically.

10 12. A method according to claim 4, wherein said polymerisation process is a free-radical polymerisation process, an ionic polymerisation process, a coordination polymerisation process or a step growth polymerisation process.

15 13. A method according to claim 4 or 5, wherein a desired size of the microspheres is achieved by controlling the nucleation and particle growth process.

20 14. A method according to claim 13, wherein the control of the nucleation and particle growth process is achieved by adjusting the composition of the functional monomer/crosslinker/solvent system and/or the reaction conditions during the polymerisation in order to change the solubility of the growing polymer chains.

15. A method according to claim 13, wherein the control of the nucleation and particle growth process is such as to avoid aggregation of the microspheres.

25 16. A method according to claim 4 or 5, wherein the size of the microspheres as produced is in the range of 0.01-10 μ m.

30 17. A method according to claim 4 or 5, wherein the reaction conditions are controlled so that the microspheres become monodisperse.

35 18. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, for screening of chemical libraries, for catalysis, for facilitating synthesis, for analyte determination using ligand binding assays and/or agglutination assays, for therapeutic purposes, or for controlled release.

19. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as stationary phase or modifier in capillary electrophoresis, capillary electrochromatography or HPLC analysis.

20. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as recognition component in biomimetic sensors.

21. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as affinity-labelled probe for targeting cells or other biological material.

22. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as binding entities for the preparation of composite materials.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : A61K 39/395, C07B 61/00, 63/00, G01N 33/531</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/41723 (43) International Publication Date: 20 July 2000 (20.07.00)</p>
<p>(21) International Application Number: PCT/SE00/00047 (22) International Filing Date: 13 January 2000 (13.01.00) (30) Priority Data: 9900121-6 14 January 1999 (14.01.99) SE (71) (72) Applicant and Inventor: MOSBACH, Klaus [SE/SE]; Lackalunga 31-38, S-244 94 Furulund (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): YE, Lei [CN/SE]; Kämnärsvägen 5D:218, S-226 46 Lund (SE). CORMACK, Peter, A., G. [GB/GB]; 56 Cartside Street, Flat 2/L, Langside, Glasgow G42 9TG (GB). (74) Agent: AWAPATENT AB; P.O. Box 5117, S 200 17 Malmö (SE).</p>		<p>(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KR (Utility model), KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>

(54) Title: MOLECULARLY IMPRINTED MICROSPHERES PREPARED USING PRECIPITATION POLYMERISATION

(57) Abstract

Molecularly imprinted microspheres comprising specific binding site are described. These microspheres can be obtained by a method comprising polymerising functional monomers and crosslinkers in a reaction solvent in the presence of print molecules as templates in a surfactant-free precipitation polymerisation process. The print molecules used are capable of forming non-covalent, reversible covalent or semi-covalent interactions with said functional monomers. There is also disclosed the use of said microspheres in different applications.



*Schematic representation of the molecular imprinting process.
(1) Pre-assembly (2) Polymerization (3) Extraction/cleavage*

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

MOLECULARLY IMPRINTED MICROSPHERES PREPARED USING
PRECIPITATION POLYMERISATION

The present invention relates to molecularly imprinted microspheres, to a method of producing said microspheres and to the use of said microspheres.

5 More particularly, the present invention relates to a method for preparing molecularly imprinted microspheres in the absence of any added surfactants. Highly specific, molecularly imprinted microspheres in the micron-scale size range can be produced quickly, cleanly and in
10 excellent yield by this method, and the regular particle size and shape of the microspheres obtained is advantageous in several ways. These artificial receptors can readily replace biologically derived receptors in many applications and are therefore highly attractive.
15 Several possible applications are described herein.

BACKGROUND OF THE INVENTION

Molecular imprinting is an established technique for the preparation of synthetic receptors with high affinities and specificities for various analytes of
20 interest. During the free-radical polymerisation commonly used in the imprinting process, the incorporation of template-complementary functionality into the polymer matrix, which is the key to ligand re-binding, is guided by the template molecules themselves, since they form
25 complementary guest-host complexes with the functional monomers. Following removal of the template from the polymer matrix, the crosslinked polymeric host can rebind the original template very specifically (Figure 1) [1-3].

Depending on the nature of the interactions guiding
30 the assembly of the guest-host complex and the subsequent recognition of the target ligand, molecular imprinting strategies can be divided into two major categories: covalent and non-covalent imprinting approaches. A semi-

covalent imprinting method is also reported, where one can use covalent interactions for the preparation of the imprinted polymer and non-covalent interactions for the subsequent re-binding of ligands of interest [4].

5 These molecularly imprinted receptor analogs are easy to produce and very stable, and are therefore superior to natural receptors in many respects.

 Molecularly imprinted polymers have been used for chromatographic separation [5], in biomimetic sensors
10 [6], in catalyzing chemical reactions [7], in solid phase extraction for sample enrichment/clean-up [8], in screening of combinatorial chemical libraries [9], for in situ product removal during biotransformation processes [10], and down-stream product purification [11]. They
15 also have great potential for drug determination using for instance ligand competition assays [12].

 Imprinted polymers are usually prepared in the form of a monolith which is then ground and sieved to the desired particle size. The grinding and sieving process
20 is time-consuming and yields only moderate amounts of useful imprinted polymer. The polymer particles obtained are also irregularly-shaped, which is not ideal for chromatographic purposes. Furthermore, the grinding process may also be detrimental to some of the binding
25 sites.

 Suspension polymerisation in perfluorocarbon liquid continuous phases has been introduced to address some of these issues [13]. Although this method delivers good yields of spherical particles with controlled particle
30 sizes, it is not a straightforward method in that it requires considerable optimisation. The perfluorocarbon dispersing phase is also somewhat expensive.

 Other imprinting methods leading to spherical particles with controlled sizes include emulsion
35 polymerisation in aqueous media, and seeded emulsion polymerisation. However, they involve either the use of

stabilisers or multi-step operations, which are neither straightforward nor broadly applicable for imprinting.

BRIEF SUMMARY OF THE INVENTION

The present invention provides a new method of
5 producing molecularly imprinted microspheres. Typically, the diameters of the microspheres are between 0.01 - 10 μm . The method is based on surfactant-free precipitation polymerisation. The specific binding sites are created using print molecules that form either non-covalent,
10 reversible covalent or "semi-covalent" interactions with the functional monomers as templates.

In the method the total volume of the polymerisable monomer/crosslinker is typically kept within 0.01 - 20% v/v that of the reaction solvent. The reaction solvent
15 employed is either aqueous or non-aqueous, and is either single component or composed of multiple solvents.

The interactions between print molecules and functional monomers utilised for imprinting and re-binding can be either reversible covalent, non-covalent,
20 or both. Multiple interactions of different characters can be simultaneously utilised. Different functional monomers can be employed simultaneously, in addition to using single functional monomers.

The solubility of the print molecules in the
25 reaction solvent can be adjusted by changing the composition of the reaction solvent.

The polymerisation can be induced by heat, by UV, by γ radiation or by chemical methods. Free-radical polymerisation, ionic polymerisation, coordination
30 polymerisation, step growth polymerisation or related methods are used to prepare molecularly imprinted microspheres without using surfactant.

Microspheres with desired particle sizes can be produced by controlling the nucleation and particle
35 growth process of the resulting polymer. This is achieved through adjusting the composition of functional monomer/crosslinker/solvent system, as well as reaction

conditions, in order to change the solubility of the growing polymer chains. The polymerisation conditions are controlled in such a way as to avoid aggregation of the microspheres.

5 The molecularly imprinted microspheres can be used as replacements for conventionally imprinted polymers in various applications. Thus, they can be used for the screening of chemical libraries, for catalysis, for facilitated synthesis, for analyte determination using
10 competitive ligand binding assays and agglutination assays.

 The microspheres can also be used as stationary phase or modifier in capillary electrophoresis, capillary electrochromatography and HPLC analysis, as recognition
15 component in biomimetic sensors, as affinity-labelled probe for targeting cells or other biological materials.

 A further use of the molecularly imprinted microspheres is as binding entities for the preparation of composite materials.

20 BRIEF DESCRIPTION OF THE DRAWINGS

 Figure 1 is a reaction scheme of a prior art molecular imprinting process.

 Figure 2 shows some examples of functional monomers which can be used in the process according to the
25 invention.

 Figure 3 shows electron micrographs of anti-17 β -estradiol microspheres prepared according to Example 3.

 Figure 4 shows the displacement of radioligand binding to molecularly imprinted microspheres under
30 equilibrium conditions, as disclosed in Example 4. B/B_0 is the ratio of the amount of radioligand bound in the presence of displacing ligand, E , to the amount bound in the absence of displacing ligand, B_0 .

 Figure 5 shows a calibration curve for theophylline,
35 as disclosed in Example 5.

 Figure 6 shows the specificity of the anti-17 β -estradiol microspheres prepared according to Example 3.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to a novel method for preparing molecularly imprinted microspheres using precipitation polymerisation, the microspheres as obtained by said method, and the applications of these imprinted microspheres.

Precipitation polymerisation, sometimes called surfactant-free polymerisation, can be used to prepare mono-disperse microspheres with controlled particle diameters typically within the 0.1-10 μm range [14-17]. The mechanism for particle formation and growth resembles that of dispersion polymerisation, except that the particles are stabilised against coagulation by their rigid, crosslinked surfaces, rather than by any added stabilisers. These microspheres are easy to prepare and are free from any adsorbed surfactants. Significantly, neither polymer grinding nor sieving steps are necessary following polymerisation, therefore the preparation of molecularly imprinted microspheres by this method is much more efficient in terms of yield and much less time-consuming to perform.

In conventional molecular imprinting protocols, the yield of imprinted polymer with the desired particle size range following successive grinding and sieving operations is usually less than 50%. In contrast, the present method allows polymer yields upwards of 85% to be attained. The regular size and shape of the particles can facilitate system homogenisation and is advantageous for mass transfer in ligand rebinding processes. It also offers benefits in chromatographic applications.

Both reversible covalent and non-covalent interactions can be utilised during the imprinting process when using precipitation polymerisation. The semi-covalent strategy can also be used. Functional monomers for reversible covalent interactions include boronate ester-forming monomers, Schiff base-forming monomers, and carbonate-forming monomers. For non-covalent inter-

actions, hydrogen bond-forming monomers, ion-pair forming monomers, metal-chelating monomers, as well as hydrophobic monomers can be used (Figure 2).

Various crosslinkers can be used depending on the solvent employed as a porogen.

Polymerisation can be initiated in a variety of ways, typically via thermal or photochemical means, and both water-soluble and organic solvent miscible initiators can be used, depending on the solvents employed.

To obtain spherical microspheres with good recognition behaviour, efficient crosslinking has to be ensured. Typically this is achieved by using a high degree of crosslinking. For some purposes, however, a much lower crosslinking density can still yield microspheres with satisfactory molecular recognition capabilities.

Compared to conventional imprinting methods, far greater amounts of solvent are used in precipitation polymerisation protocols to prepare the imprinted microspheres. Both aqueous and non-aqueous solvents can be used for different target print molecules. When the non-covalent strategy is used, except where the hydrophobic effect is of interest, less-polar organic solvents, for example dichloromethane and acetonitrile are generally most satisfactory. Imprinting via other strategies can readily use aqueous and polar non-aqueous solvents. The total monomer volume in the polymerization solution is generally within the range of 1 - 10% v/v with respect to the polymerisation solvent, to prevent aggregation of the microspheres.

The amount of print molecule can be, though not necessarily, so high as to saturate the solvent containing the functional monomer and the crosslinker at the polymerisation temperature in order to provide a high load capacity for the resulting imprinted microspheres.

On the other hand, a poor solvent for the print molecule can be introduced as a co-solvent, if required, to reduce the solubility of the print molecule and therefore to reduce the amount of print molecule required. This may be an attractive approach when one is using an expensive print molecule, for example, hexane can be added to acetonitrile to make the print molecule much less soluble while the complex formation between the functional monomer and the print molecule in the non-covalent approach is not sacrificed.

By controlling various reaction conditions, such as the solubility parameters of the resulting polymer and that of the solvent, the nucleation and growth behaviour of the polymer particles can be tailored to deliver microspheres of controlled particle diameter and porosity that retain high affinity and specificity for the print molecules.

The molecularly imprinted microspheres can be used in various applications. These artificial receptors can readily replace their natural counterparts in many instances. Their regular size and shape allows better reproducibility in different assays. Non-limiting examples of applications of molecularly imprinted microspheres, including monodisperse microspheres, are:

- 1) as stationary phases or modifiers in capillary electrophoresis;
- 2) as recognition components in biomimetic sensors;
- 3) as catalysts to facilitate chemical/biochemical reactions;
- 4) as probes for cell or other biological material targeting in which case they are dyed or made magnetic;
- 5) for drug determination using competitive ligand assay;
- 6) as bio-compatible carrier for controlled drug release;
- 7) as binding components to prepare composite materials for affinity purification/isolation of target compounds.

The invention will now be described more in detail by way of the following non-limiting examples.

EXAMPLE 1*Preparation of anti-theophylline microspheres*

Acetonitrile (50 mL) is mixed with methacrylic acid (MAA, 372.5 mg) and trimethylolpropane trimethacrylate (TRIM, 627.5 mg) in a borosilicate glass tube. Theophylline (115 mg) is suspended in the solution and dissolved after sonication at 60°C. The initiator, azobisisobutyronitrile (AIBN, 17.5 mg) is dissolved, the solution purged with nitrogen for five minutes and the tube sealed under nitrogen. Polymerisation is induced by placing the tube in a water bath preset at 60°C and continued for 24 hours.

The microspheres formed are collected by centrifugation at 8000 rpm for 10 minutes using a RC5C superspeed refrigerated centrifuge from BECKMAN (Palo Alto, CA, USA). The print molecule is thoroughly extracted by washing repeatedly with methanol containing 10% acetic acid (v/v), followed by a final wash in acetone. These successive centrifugation and decanting steps extract the print molecule from the polymer. The anti-theophylline microspheres obtained are monodisperse and have an average diameter of 0.2 μm . The microspheres are finally dried *in vacuo*. The reference (control) microspheres are prepared and treated in exactly the same way, except that no print molecule is used in the polymerisation stage.

EXAMPLE 2*Preparation of anti-theophylline microspheres*

Acetonitrile (50 mL) is mixed with MAA (372.5 mg) and TRIM (627.5 mg) in a borosilicate glass tube. Theophylline (11.5 mg) and AIBN (17.5 mg) are dissolved in the solution. The solution is purged with nitrogen for five minutes and the tube sealed under nitrogen. Polymerisation is induced by UV irradiation (350 nm) at 20°C using a RMA-400 Rayonet photochemical reactor from Southern New England Ultraviolet Co. (Bradford, CT, USA) and continued for 24 hours.

The microspheres obtained are treated in the same way as in example 1 to remove the print molecule. The reference (control) microspheres are prepared and treated in exactly the same way, except that no print molecule is used in the polymerisation stage.

EXAMPLE 3

Preparation of anti-17 β -estradiol microspheres

Acetonitrile (50 mL) is mixed with MAA (372.5 mg) and TRIM (627.5 mg) in a borosilicate glass tube. 17 β -Estradiol (250 mg) and AIBN (17.5 mg) are dissolved in the above solution. The solution is purged with nitrogen for five minutes and the tube sealed under nitrogen. Polymerisation is induced by UV irradiation (350 nm) at 20°C using a RMA-400 Rayonet photochemical reactor from Southern New England Ultraviolet Co. (Bradford, CT, USA) and continued for 24 hours.

The microspheres obtained are treated in the same way as per example 1 to remove the print molecule. The anti-17 β -estradiol microspheres obtained are monodisperse and have an average diameter of 0.3 μ m (Figure 3). The reference (control) microspheres are prepared and treated in exactly the same way, except that no print molecule is used in the polymerization stage.

EXAMPLE 4

Competitive radioligand assay using anti-theophylline microspheres from example 1

The binding capacity of the anti-theophylline microspheres from example 1 is estimated from saturation studies. Varying amounts of the microspheres are incubated overnight and at room temperature with 16.2 pmol (685 Bq) [8-³H]theophylline in 1 mL acetonitrile, using polypropylene microcentrifuge tubes. A rocking table ensured gentle mixing.

The microspheres are then separated by centrifugation at 14,000 rpm for five minutes, 500 μ L supernatant mixed with 10 mL scintillation liquid, Ecoscint O (National Diagnostics, Manville, NJ, USA), and

the radioactivity then measured using a model 2119
BACHBETA β -radiation counter from LKB Wallac (Solentuna,
Sweden). The amount of anti-theophylline microspheres
required to bind half of the added radioligand is
5 estimated to be 5 mg, while an equivalent amount of the
reference polymer binds less than 10% of the added
radioligand.

The theophylline-imprinted microspheres are
suspended in acetonitrile (25 mg/mL) and sonicated to
10 form a polymer stock suspension, from which 200 μ L was
transferred into each microcentrifuge tube. Varying
amounts of non-radiolabelled ligand, including
theophylline, theobromine, xanthine and caffeine, and
16.2 pmol (685 Bq) [8- 3 H]theophylline are added, and the
15 final volume adjusted to 1 mL with acetonitrile. The
competitive binding is allowed to proceed overnight by
incubation at ambient temperature, using a rocking table
for gentle mixing. The amount of bound radioligand is
estimated by measuring the radioactivity from 500 μ L
20 supernatant following centrifugation at 14,000 rpm for
five minutes. The high specificity of the anti-
theophylline microspheres can be evaluated by comparing
the IC_{50} value of compounds closely related to the print
molecule, with IC_{50} being the ligand concentration that
25 can displace 50% of the bound radioligand from the
imprinted microspheres. Figure 4 shows the displacement
of radioligand binding to molecularly imprinted
microspheres under equilibrium condition. B/B_0 is the
ratio of the amount of radioligand bound in the presence
30 of displacing ligand, B , to the amount bound in the
absence of displacing ligand, B_0 .

EXAMPLE 5

*Competitive radioligand assay using anti-theophylline
microspheres from example 2*

35 The same procedure as used in example 4 is followed,
except that the microspheres are from example 2. The
amount of anti-theophylline microspheres required to bind

half of the added radioligand is estimated to be 10 mg, while an equivalent amount of the reference polymer binds less than 20% of the added radioligand.

The theophylline-imprinted microspheres are
5 suspended in acetonitrile (50 mg/mL) and sonicated to form a polymer stock suspension, from which 200 μ L was transferred into each microcentrifuge tube. The same competitive binding assay as in example 4, using theophylline as the cold ligand, is followed. A
10 calibration curve for theophylline similar to the one in Figure 4 is obtained, although the non-specific binding is slightly higher (Figure 5).

EXAMPLE 6

*Competitive radioligand assay using anti-17 β -estradiol
15 microspheres from example 3*

Varying amounts of the microspheres were incubated overnight and at room temperature with 417 fmol (1110 Bq) [2,4,6,7- 3 H(N)]estradiol in 1 mL acetonitrile, using polypropylene microcentrifuge tubes. Other conditions are
20 the same as used in example 4. The amount of anti-17 β -estradiol microspheres required to bind half of the added radioligand is estimated to be 30 mg, while an equivalent amount of the reference polymer binds less than 12% of the added radioligand.

25 The 17 β -estradiol-imprinted microspheres are suspended in acetonitrile (150 mg/mL) and sonicated to form a polymer stock suspension, from which 200 μ L was transferred into each microcentrifuge tube. Varying amounts of non-radiolabelled ligand, including 17 β -
30 estradiol, 17 α -estradiol and 17 α -ethynylestradiol, and 417 fmol (1110 Bq) [2,4,6,7- 3 H(N)]estradiol are added, and the final volume adjusted to 1 mL with acetonitrile. Other conditions are the same as used in example 4. The specificity of the anti-17 β -estradiol microspheres is
35 signified in Figure 6.

REFERENCES

- (1) Mosbach, K.; Ramström, O. *Bio/Technology* 1996, 14, 163-170.
- (2) Wulff, G. *Angew. Chem. Int. Ed. Engl.* 1995, 34, 1812-1832.
- (3) Shea, K. J. *Trends in Polymer Science* 1994, 2, 166-173.
- (4) Whitcombe, M.; Rodriguez, M.; Villar, P.; Vulfson, E. *J. Am. Chem. Soc.* 1995, 117, 7105-7111.
- (5) Kempe, M. *Anal. Chem.* 1996, 68, 1948-1953.
- (6) Kriz, D.; Ramström, O.; Svensson, A.; Mosbach, K. *Anal. Chem.* 1995, 67, 2142-2144.
- (7) Müller, R.; Andersson, L. I.; Mosbach, K. *Makromol. Chem. Rapid Commun.* 1993, 14, 637-641.
- (8) Sellaergren, B. *Anal. Chem.* 1994, 66, 1578-1582.
- (9) Ramström, O.; Ye, L.; Krook, M.; Mosbach, K. *Anal. Commun.* 1998, 35, 9-11.
- (10) Ye, L.; Ramström, O.; Månsson, M.-O.; Mosbach, K. *J. Mol. Reg.* 1998, 11, 1-4.
- (11) Ye, L.; Ramström, O.; Mosbach, K. *Anal. Chem.* 1998, 70, 2789-2795.
- (12) Vlatakis, G.; Andersson, L. I.; Müller, R.; Mosbach, K. *Nature* 1993, 361, 645-647.
- (13) Mayes, A.; Mosbach, K. *Anal. Chem.* 1996, 68, 3769-3774.
- (14) Naka, Y.; Kaetsu, I.; Yamamoto, Y.; Hayashi, K. *J. Polym. Sci.: Part A: Polym. Chem.* 1991, 29, 1197-1202.
- (15) Naka, Y.; Yamamoto, Y. *J. Polym. Sci.: Part A: Polym. Chem.* 1992, 30, 1287-1298.
- (16) Li, K.; Stöver, D. H. *J. Polym. Sci.: Part A: Polym. Chem.* 1993, 31, 3257-3263.
- (17) Li, W.-H.; Stöver, D. H. *J. Polym. Sci.: Part A: Polym. Chem.* 1998, 36, 1543-1551.

CLAIMS

1. Molecularly imprinted microspheres comprising specific binding sites, obtainable by polymerising functional monomers and crosslinkers in a reaction solvent in the presence of print molecules as templates in a surfactant-free precipitation polymerisation process, which print molecules are capable of forming non-covalent or reversible covalent interactions with said functional monomers.

2. Molecularly imprinted microspheres according to claim 1, the diameter of which are within the range of 0.01 to 10 μ m.

3. Molecularly imprinted microspheres according to claim 1, which are monodisperse.

4. A method of producing molecularly imprinted microspheres comprising specific binding sites, characterised by polymerising functional monomers and crosslinkers in a reaction solvent in the presence of print molecules as templates in a surfactant-free precipitation polymerisation process, which print molecules are capable of forming non-covalent or reversible covalent interactions with said functional monomers.

5. A method according to claim 4, wherein the total volume of polymerisable monomers and crosslinkers is kept in the range of about 0.01 to 20 % of the volume of the reaction solvent.

6. A method according to claim 4 or 5, wherein the reaction solvent is aqueous or non-aqueous.

7. A method according to claim 4 or 5, wherein said reaction solvent is composed of a single solvent component or of multiple solvent components.

8. A method according to claim 4, wherein said functional monomers have the same functionality.

9. A method according to claim 4, wherein said functional monomers have different functionality.

10. A method according to claim 4 or 5, wherein the solubility of the print molecules in the reaction solvent is adjusted by changing the composition of the reaction solvent.

5 11. A method according to claim 4, wherein the polymerisation is induced by heat, UV radiation, γ radiation and/or chemically.

12. A method according to claim 4, wherein said polymerisation process is a free-radical polymerisation process, an ionic polymerisation process, a coordination polymerisation process or a step growth polymerisation process.

13. A method according to claim 4 or 5, wherein a desired size of the microspheres is achieved by
15 controlling the nucleation and particle growth process.

14. A method according to claim 13, wherein the control of the nucleation and particle growth process is achieved by adjusting the composition of the functional monomer/crosslinker/solvent system and/or the reaction
20 conditions during the polymerisation in order to change the solubility of the growing polymer chains.

15. A method according to claim 13, wherein the control of the nucleation and particle growth process is such as to avoid aggregation of the microspheres.

25 16. A method according to claim 4 or 5, wherein the size of the microspheres as produced is in the range of 0.01-10 μ m.

17. A method according to claim 4 or 5, wherein the reaction conditions are controlled so that the
30 microspheres become monodisperse.

18. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, for screening of chemical libraries, for catalysis, for facilitating synthesis, for
35 analyte determination using ligand binding assays and/or agglutination assays, for therapeutic purposes, or for controlled release.

19. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as stationary phase or modifier in capillary electrophoresis, capillary electro-
5 chromatography or HPLC analysis.

20. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as recognition component in biomimetic sensors.

10 21. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as affinity-labelled probe for targeting cells or other biological material.

15 22. Use of the molecularly imprinted microspheres as defined in any one of claims 1-3, or prepared according to any one of claims 4-17, as binding entities for the preparation of composite materials.







FIGURE 1. *Schematic representation of the molecular imprinting process.*
(1) *Pre-assembly* (2) *Polymerization* (3) *Extraction/cleavage*

Boronate ester-forming monomer


4-Vinylphenylboronic acid

Hydrogen bond-forming and ion-pair forming monomers


Methacrylic acid



4-Vinylpyridine


Metal-chelating monomers

4-Vinyl imidazole




4-Vinylbenzyl-iminoacetic acid

FIGURE 2



Magnification 7,500 x

FIGURE 3a



Magnification 30,000 x

FIGURE 3b




FIGURE 4




FIGURE 5




FIGURE 6

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 00/00047

A. CLASSIFICATION OF SUBJECT MATTER

IPC7: A61K 39/395, C07B 61/00, C07B 63/00, G01N 33/531
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbol(s))

IPC7: A61K, C07B, G01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	Journal of Polymer Science:Part A:Polymer Chemistry, Volume 31, 1993, Kai Li et al, "Synthesis of Monodisperse Poly(divinylbenzene) Microspheres" page 3257 - page 3263 --	1-13
X	WO 9738015 A1 (IGEN, INC.), 16 October 1997 (16.10.97) -- -----	1-13

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier document but published on or after the international filing date
 "I" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
 "&" document member of the same patent family

Date of the actual completion of the international search

25 May 2000

Date of mailing of the international search report

30 -05- 2000

Name and mailing address of the ISA:

Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Anna Sjölund/Eö
Telephone No. +46 8 782 25 00

Information on patent family members

02/12/99

International application No.

PCT/SE 00/00047

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9738015 A1	16/10/97	AU 2721797 A	29/10/97
